



BONA PRIME INTENSE

Sitework

Surface preparation

The surface which is to be coated must be sanded back to bare wood, dry and free from sanding dust, oil, wax and other contamination. The Bona Scrad system, Bona Sanding Screen or abrasive grade no. 120 or finer should be used for the final sanding of the wood. The best results are obtained using a Bona Buffer.

Application

Ensure that the container is shaken thoroughly prior to use (or before decanting smaller quantities). It is suggested that application is carried out using a Bona roller or a Bona Applicator. Apply the finish evenly with a smooth flowing action avoiding accumulations of finish.

Note: The room and finish temperature must not fall below +13°C during application and drying.

Application rate: 8-10 m²/litre (120-100 g/m²).

Drying time: 1-2 hours at 20°C/60% RH.

After the application of Bona Prime Intense a light sanding may be carried out to cut back grain raise using the Bona Scrad system or Bona Sanding Screen grade no. 120 or finer.

Bona Prime Intense can be overcoated with all Bona waterborne finishes.