



BONA SPORTIVE PAINT

Sitework

Surface preparation

The surface which is to receive sports lines/paint should be coated with Bona Sportive system, or other Bona waterborne finishes. The sports paints are applied on to the second or latter application of finish. Allow the finish to dry then lightly sand the surface and carefully clean to remove dust, etc. Use the Bona Scrad system, sanding disc/screen or sandpaper grade no. 120 or finer. Courts and lines should be marked with suitable lining tape pressed firmly to the floor.

Factory pre-finished floors and previously finished old floors

Sportive Paint usually has good adhesion to pre-finished and previously finished floors but the intercoat adhesion should be checked prior to application of the paint and overcoating: see Bona Prep information.

Application

Stir Sportive Paint thoroughly prior to use.

Apply the paint evenly using a roller or brush for waterborne paint. Poor coverage will affect the opacity/hiding ability. Several applications may be needed in some circumstances. **Note:** The room and paint temperature must not fall below +13°C during application and drying. For best results remove the lining tape while the paint is still wet..

After Sportive Paint has dried thoroughly it should be lightly sanded to provide a physical key for subsequent applications of finish. An application of Sportive Finish may usually be made 24 hours after the paint has dried.

Colours:	Black / White / Blue / Light Blue / Red / Orange / Green / Yellow
Application rate:	Approx 4 m ² / litre
Drying time:	Drying - 1 hour at 20°C/60% RH. Overcoating - 24 hours at 20°C/60% RH
Cleaning:	Tools - water immediately after application. Use acetone for dried finish. Residues - allow to dry prior to disposal. Do not pour into the drainage system.